

XENOLITE Strata+ 300 Series Bi-Layer

XENOLITE Strata+ 300 Series is a lead-free, lightweight, flexible and recyclable x-radiation protection material, using two attenuating elements, one low Atomic Weight ("Z") element and one high Z element, in a layered combination optimized for minimum area-weight and maximum attenuation in the key diagnostic imaging range of 60/70/90/110 kV, representing the scatter from X-Ray tubes having 60-125kV tube voltage.

K-EDGE AND LAYERING TECHNOLOGY

STRATA+'s lighter weight results from the use of the two attenuating elements. The low Z element gives more efficient attenuation of the lower energy photon spectrum below the K-edge window of lead (35-88 keV), complemented by the higher Z element -bismuth- which is more efficient for stopping higher energy radiation (> 88 keV). The layering of the high Z element (nearest the body) also virtually eliminates secondary radiation/fluorescence from the outer layer.

COMBINED WITH ADVANCED POLYMER TECHNOLOGY

The attenuating elements, in fine powder form, are supported, encapsulated and homogeneously distributed in a tough but flexible, high-tech plasticized elastomer matrix. This Dow-DuPont developed elastomer has the best balance of toughness, flexibility, durability and cracking resistance and is more commonly used for the flexing components of running shoes and vibration pads. Separate layers, not laminated, give much better flexibility, drape and fit.

ENVIRONMENTAL BENEFITS

Strata+ lead-free material is not "cross-linked" or "cured" and is therefore fully recyclable and thermally re-processable, or may be disposed of as a non-hazardous, non-toxic waste in municipal landfills.

SPECIFICATIONS

Protection 0.50, 0.35 and 0.25 mm Pb equivalence*
Weight: 5.75 kg/sq m (0.50 mm Pb)

	60 kV	70 kV	90 kV	110 kV
0.50mm Pb	0.4%	0.9%	3.3%	5.3%
0.35mm Pb	0.9%	2.2%	6.0%	9.2%
0.25mm Pb	2.5%	4.4%	9.9%	14.4%

*Test Method: IEC 61331-1:2014 (BBG); 60/70/90/110 kV

MADE IN THE USA 



975 Madison Avenue
Norristown, PA 19403

T: (610) 650-8690
(800) 647-5483

info@xenolitexray.com
xenolitexray.com

F: (610) 650-8694